



TIKKURILA

SUPI SAUNASUOJA

SAUNA FINISH FOR PANELS / TINTABLE

DESCRIPTION

Tintable acrylic protective agent.

RECOMMENDED USES

Especially suitable for walls and ceilings in steam, washing and dressing rooms.

PRODUCT FEATURES

For the surface treatment of humid interior spaces. Forms a dirt- and water-repellent coating. Contains an anti-mold agent that protects the treated surface. Suitable for the treatment of wooden, wood fiberboard and concrete surfaces. Not suitable for the treatment of sauna benches.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

SUPI SAUNASUOJA

TECHNICAL DATA	
Base paints	EP BASE
Colour Shades	Color cards: Interior wood stains and lacquers colour card, Tikkurila Timeless Translucent Can be tinted in Tikkurila translucent colors.
Gloss	Semi-matt.
Coverage	8–12 m ² /l.
Can sizes	0.9 l, 2.7 l, 9 l
Application method	Brush or spray.
Drying time	Dust dry after approx. 30 minutes. Recoatable after 2–3 hours. Ready for use in approx. 48 hours.
Density (kg/l)	1.0 kg/l, ISO 2811.
Volume solids (%)	16
VOC	(cat A/f) 130g/l(2010) Supi Saunasuoja contains VOC max. 130 g/l.
Storage	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



SUPI SAUNASUOJA

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry, the ambient temperature at least +5 °C and the relative humidity of air below 80%.

Surface preparation

New clean wood surfaces:

Clean the wood surface of any dirt and dust. Wet the surface lightly with water spray, let dry and sand off the loose wood fibers. Remove the sanding dust.

Old and dirty surfaces or surfaces previously treated with, e.g. Supi Saunasuoja:

Wash with Supi Saunapesu cleaning agent according to instructions, rinse thoroughly and let dry. Sand if necessary and remove the sanding dust.

Application

Stir Supi Saunasuoja thoroughly before and occasionally during use.

Apply one coat of tinted or untinted Supi Saunasuoja on the walls of the steam room. Thin with water, if necessary.

You can also apply two coats of tinted Supi Saunasuoja thinned 50% with water on the walls of the steam room. This way, the brush marks will be less noticeable.

Apply two coats of Supi Saunasuoja on the wood surfaces in the washing and dressing rooms. Thin tinted Supi Saunasuoja approx. 20% with water for the first application. Only thin the clear Supi Saunasuoja if necessary.

First test the tinted Supi Saunasuoja in an inconspicuous area to ensure that you have the right color. When the product is thinned, the color becomes slightly lighter and more translucent than in the color card. The final color depends on the properties and any previous treatment of the wood. For achieving a uniform color, treat small surfaces entirely without interruptions; with large panel surfaces, treat 1–2 panels at a time.

Pre-heat the sauna and ventilate it well before use.

Note

Pre-heat the sauna before taking into use and ventilate it well.

Cleaning of tools

Clean the tools with water and soap. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint. Clean the tools with water and soap. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

If needed, after approx. 1 month from surface treatment, at the earliest:

Clean the surface with Supi Saunapesu (mix 1–2 dl of Saunapesu with 5 l of water).

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



SUPI SAUNASUOJA

Recycle empty, dry cans or dispose them of in accordance with local regulations.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



SUPI SAUNASUOJA

Health and Safety

Harmful to aquatic life with long lasting effects. Avoid release to the environment. Wear protective gloves. Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)) and 2-octyl-2H-isothiazol-3-one (OIT). May produce an allergic reaction. This surface treatment agent contains a biocidal product for the preservation of the dry film. Contains OIT and 3-iodo-2-propynyl butylcarbamate (IPBC). This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT (3:1).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.