

Temaflor AC502

DESCRIPTION

A two-component, solvent-free, elastic acrylic binder.

PRODUCT FEATURES AND RECOMMENDED USES

- Used as a binder for Temaflor AC acrylic troweling screed.
- Suitable to be used as a self-levelling coating and as a binder of a coloured sand screed.
- Suitable also for indoor asphalt floors.
- Mixed with sand also suitable for patching of concrete floors.
- Cures fast also in low temperatures.
- Recommended for the floors of engineering workshops, warehouses, cold stores of food industry parking deck surfaces, loading ramps and terraces.

TECHNICAL DATA

Volume solids

approx. 100%

Specific gravity

0.98 kg /l (ready made mixture)

Mixing ratio

Temperature (°C)*	The amount of hardener (percentage of weight of the binder)	Pot life (min)	Drying time (min)
+5	5	ab. 25	ab. 70
+10	4	ab. 25	ab. 60
+20	2	ab. 25	ab. 45
+30	1	ab. 25	ab. 50

* Temperature of the binder, air and the floor.

Self-levelling screeds 5–6 mm:

Temaflor AC502 30 w-%

Coloured sand Ø 0,1–0,6 mm 30 w-%

Coloured sand Ø 0,3–0,8 mm 40 w-%

Surface is fully broadcast with coloured sand Ø 0.6–1.2 mm.

Possible hardeners

BP-50-FT, Perkadox®CH-50 or PEROXAN BP-Pulver 50 W.

Practical coverage

For a flat substrate:

2 mm layer: 2 litres ready for use screed / m²

6 mm layer: 6 litres ready for use screed / m²

Practical coverage depends on the evenness of the substrate.

Cleaning of equipment

Thinner 006 1400.

Finish

Semi-matt.

Colors

The colour of the screed is determined by the sand used.

Thinning instructions

Do not thin.

VOC

VOC 2004/42/EC (cat A/j), 500 g/l (2010)

Temaflor AC502: max. VOC < 500 g/l.

Can sizes

200 KG

Temafloor AC502

APPLICATION INSTRUCTIONS

Surface preparation	Always remove all grease, oil, and other impurities with Maalipesu detergent before grinding. Remove laitance or old peeling paint layers by power grinding, milling, or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot holes removing all loose or brittle material. Open cracks with e.g. an abrasive tool. After mechanical pre-treatment remove all loose material and dust carefully with a vacuum cleaner. The substrate must have a tensile strength above 1.5 MPa. For application on cementitious leveling screed: check compatibility with the leveling screed manufacturer.
Application conditions	The relative humidity of the concrete should not exceed 97%. Residual moisture content should be below 4 weight-%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80%.
Mixing components	First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.
Priming	Prime using Temafloor AC102 Primer. Pour the primer mixture onto the floor and apply by the trowel or roller as much as is needed to impregnate the concrete surface. If necessary, repeat priming to get a non-porous surface. A porous priming coat will result in holes and air bubbles in the finished coating. Subsequent treatment can be carried out after 30 min. Scatter sand of grain size Ø 0,4–0,8 mm on the fresh primer coat to ensure the screed adhesion and prohibit gliding of the screed.
Patching	Patch pot-holes and cracks with a mixture of unthinned Temafloor AC502 and dry, clean sand. Mixing ratio e.g. 1 part by volume of varnish mixture and 1–2 parts by volume of sand of grain size 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary. The floor can be levelled by using Temafloor AC502 and sand of grain size 0,5–1,2 mm. Note! Concrete surface should always be primed before patching.
Screed	Pour the Temafloor AC502 mixture onto the floor. Apply by an adjustable trowel to the desired thickness. Trowel the screeded surface by hands or use broadcasting technique.
Topcoating	Topcoating can be carried out after the screed has cured. Topcoating can be carried out with Temafloor AC602 Clear topcoat. Pour the varnish mixture onto the floor, apply with a rubber trowel and level with a roller. Note! Add the remaining mixture to the next batch of the product, do not scrape it out of the container onto the floor.

HEALTH AND SAFETY	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oyj.
--------------------------	--

For professional use only.



Temafloor AC502

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

Temafloor AC502

EN 13813

The European harmonized product standard EN 13813:2002 defines the requirements for Screed materials and floor screeds, including synthetic resin screeds.

This product is tested and CE-labelled in accordance with the tables ZA.1.5 and ZA.3.3 in the appendix ZA.3.

CE	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
13	
TIK-1600-5003b	
EN 13813 SR-B2,0-AR 0,5-IR 4	
Synthetic resin screed.	
Impact resistance	IR4
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot h^{0,5}$
Chemical resistance	Class 1
Release of corrosive substances	SR
Abrasion resistance	AR 0,5
Thermal resistance	NPD
Reaction to fire	E _{fl} (NPD)
Adhesion strength by pull off test	B 2,0
Release of dangerous substances	NPD
Sound absorption	NPD
Sound insulation	NPD

Tested as part of a system together with Temafloor AC102 Primer and Temafloor AC602 Clear.

Temafloor AC502

EN 1504-2:2004

Eiropas saskaņotais produktu standarts EN 1504-2:2004 nosaka prasības betona virsmas aizsardzības sistēmām.

Šis produkts ir testēts un marķēts ar CE zīmi saskaņā ar ZA pielikuma tabulām 1d, 1f un 1g.

CE	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
0809-CPD-0773	
TIK-1600-5003a	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO ₂	$s_D > 50 \text{ m}$
Impact resistance	Class I: $\geq 4 \text{ Nm}$
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot h^{0,5}$
Abrasion resistance	$< 3000 \text{ mg}$
Reaction to fire	E _{fl} -s1 (NPD)
Adhesion strength by pull off test	$\geq 2,0 \text{ N/mm}^2$
Release of dangerous substances	NPD
Permeability to water vapour	Class III, $s_D > 50 \text{ m}$
Resistance to severe chemical attack	Class I

Tested as part of a system together with Temafloor AC102 Primer and Temafloor AC602 Clear.